



SUBJECT Microbiological Test

TEST LOCATION TÜV SÜD China

TÜV SÜD Products Testing (Shanghai) Co., Ltd.
B-3/4, No.1999 Du Hui Road, Minhang District
Shanghai 201108, P.R. China

CLIENT NAME ASUSTeK Computer Inc.

CLIENT ADDRESS 3F, No.287, Niupu Rd., Xiangshan Dist, IF, No.15, I-ide Rd., 112 Beitou Dist. Taiwan
City, Taiwan

TEST PERIOD 22-Jun-2026~30-Jun-2026

TEST REQUEST Antibacterial Test- with reference to ISO 22196:2011

COMMENT 7216016401-3&4:
1.The Log values of antimicrobial activity for *Escherichia coli* of the products is 0.
2.The Log values of antimicrobial activity for *Staphylococcus aureus* of the products is 0.

Prepared By

(Fancy Fan)
Report Drafter

Authorized By

(Claire Chen)
Authorized Signatory

Note: (1) The TÜV SÜD Certification and Testing (China) Co., Ltd. "General Terms & Conditions" applied." .For full version, please visit:
<https://www.tuvsud.com/en/terms-and-conditions>

(2) The results in this report are relevant only to the sample(s) tested.

(3) The test report may not be reproduced in part without written approval of the laboratory.

(4) Disclaimer Measurement Uncertainty:

Unless otherwise agreed upon, Pass or Fail verdicts are given based on the measured values without any considerations of measurement uncertainties.

Please note, every test method has a measurement uncertainty which has been evaluated by the laboratory according to ISO/IEC 17025 requirements.

By taking measurement uncertainties into account it might happen that measured values can neither be assessed as Pass nor as Fail.

(5) The testing report without CMA stamp is not legally binding and could only be used as internal reference material for the applicant. It shall not be provided as a notarial certification.

SAMPLE SOURCE/ RECEIPT DATE / TEST DATE

Logistics Express / 22-Jun-2026/22-Jun-2026

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED

BY/ ON BEHALF OF THE CLIENTS AS

Sample Name: LCD Monitor

Batch No./Date: /

Manufacturer: /

SAMPLE NO.	SAMPLE TYPE/ SPECIFICATION	DESCRIPTION	PHOTOGRAPH
7216016401-3	VY249HG2 (金髮(PCS-FNT633))	Black sheet	
7216016401-4	VY249HG2 (UNIC(ABF-1030G))	Black sheet	

TEST METHOD(S)

Antibacterial Test

- with reference to ISO 22196:2011 Measurement of antibacterial activity on plastics and other non-porous surfaces

TEST ORGANISM(S)

Escherichia coli ATCC 8739

Staphylococcus aureus ATCC 6538P

TEST RESULT(S)

Name of test bacteria	Concentration of bacteria (CFU/mL)	The average(cells/cm ²) of the common Logarithm of the number of viable bacteria recovered			Log value of antimicrobial activity
		/	at "0h" contact time	at "24h" contact time	
<i>Escherichia coli</i> ATCC 8739	7.0×10 ⁵	7216016401-3	/	6.4	0
		Control Sample	3.9	6.3	
<i>Staphylococcus aureus</i> ATCC 6538P	7.8×10 ⁵	7216016401-3	/	6.1	0
		Control Sample	3.9	6.0	

Name of test bacteria	Concentration of bacteria (CFU/mL)	The average(cells/cm ²) of the common Logarithm of the number of viable bacteria recovered			Log value of antimicrobial activity
		/	at "0h" contact time	at "24h" contact time	
<i>Escherichia coli</i> ATCC 8739	7.0×10 ⁵	7216016401-4	/	6.4	0
		Control Sample	3.9	6.3	
<i>Staphylococcus aureus</i> ATCC 6538P	7.8×10 ⁵	7216016401-4	/	6.1	0
		Control Sample	3.9	6.0	

Note:

1. The control sample is provided by TÜV SÜD laboratory.
2. Preparation of test specimens by wiping with 70% ethanol in water.
3. The volume of the test inoculum used is 0.2 mL. The surface area of the cover film is 1600 mm².
4. 0.05% Polysorbate80 was added to the test inoculum.
5. Comment: **FAIL** for *Escherichia coli* and *Staphylococcus aureus*.

Limit is provided by client, with reference to JIS Z 2801:2012 : If the value of antibacterial activity more than 2.0 indicates the tested product with antibacterial effectiveness.

-END OF THE TEST REPORT-